Newcastle University e-prints

Date deposited: 26th November 2012

Version of file: Author final

Peer Review Status: Peer reviewed

Citation for item:

Gosling PD, Bridgens BN, Albrecht A, Alpermann H, Angeleri A, Barnes M, Bartle N, Canobbio R, Dieringer F, Gellin S, Lewis W, Mageau N, Mahadevan R, Marion J-M, Marsden P, Milligan E, Phang YP, Sahlin K, Stimpfle B, Suire O, Uhlemann J. [Analysis and design of membrane structures: results of a round robin exercise](#). *Engineering Structures* 2012, **48**, 313-328.

Further information on publisher website:

<http://www.sciencedirect.com>

Publisher's copyright statement:

© Elsevier, 2012.

Authors retain the right to voluntarily post their article 'on open web sites operated by author or author's institution for scholarly purposes'.

The definitive version of this article is available at:

<http://dx.doi.org/10.1111/j.1474-9726.2012.00795.x>

Always use the definitive version when citing.

Use Policy:

The full-text may be used and/or reproduced and given to third parties in any format or medium, without prior permission or charge, for personal research or study, educational, or not for profit purposes provided that:

- A full bibliographic reference is made to the original source
- A link is made to the metadata record in Newcastle E-prints
- The full text is not changed in any way.

The full-text must not be sold in any format or medium without the formal permission of the copyright holders.

<p>Robinson Library, University of Newcastle upon Tyne, Newcastle upon Tyne. NE1 7RU. Tel. 0191 222 6000</p>
--

Analysis and design of membrane structures: results of a round robin exercise

P.D. Gosling¹, B.N. Bridgens^{1*}, A. Albrecht², H. Alpermann³, A. Angeleri⁴, M. Barnes⁵, N. Bartle¹, R. Canobbio⁴, F. Dieringer⁶, S. Gellin⁷, W.J. Lewis⁸, N. Mageau⁹, R. Mahadevan¹⁰, J-M. Marion¹¹, P. Marsden¹², E. Milligan¹³, Y.P. Phang¹⁴, K. Sahlin¹⁵, B. Stimpfle¹⁶, O. Suire¹⁷, J. Uhlemann¹⁸.

*Corresponding author: ben.bridgens@ncl.ac.uk, +44(0)191 222 6409. Full address: Newcastle University, School of Civil Engineering & Geosciences, Drummond Building, Newcastle-upon-Tyne, NE1 7RU, UK

¹ School of Civil Engineering & Geosciences, University of Newcastle, Newcastle-upon-Tyne, NE1 7RU, UK

² Elioth, EGIS Concept, 4 rue Dolorès Ibarruri, TSA 80006, 93188 Montreuil Cedex, France

³ University of the Arts Berlin, Faculty of Architecture, Chair of structural design and technology, Hardenbergstrasse 33, 10623 Berlin, Germany

⁴ CANOBBIO SpA, Via Roma 3, 15053 Castelnuovo Scrivia (AL) Italy

⁵ Department of Architecture & Civil Engineering, University of Bath, Bath, BA2 7AY, UK

⁶ TU München, Chair of Structural Analysis, Arcisstr. 21, 80333 Munich, Germany

⁷ Buffalo State College, 1300 Elmwood Avenue, Buffalo NY 14222, USA

⁸ School of Engineering, University of Warwick, Library Road, Coventry CV4 7AL, UK

⁹ schlaich bergemann und partner, Schwabstrasse 43, 70197 Stuttgart, Germany

¹⁰ Techno Specialist (FZE), P.O. Box 121908, SAIF Zone, Sharjah, UAE

¹¹ AIA Ingénierie, 20 rue Lortet, 69341 Lyon Cedex 07, France

¹² Buro Happold, Camden Mill, 230 Lower Bristol Road, Bath, BA2 3DQ, UK

¹³ Tensys Limited, 1 St Swithins Yard, Walcot St, Bath, BA1 5BG, UK

¹⁴ Multimedia Engineering Pte Ltd, 50 Bukit Batok St 23 #05-15, Singapore

¹⁵ Radome Modeling Team, Saint-Gobain Performance Plastics, 701 Daniel Webster Hwy, Merrimack, NH, 03054, USA

¹⁶ form TL ingenieure für tragwerk und leichtbau gmbh, Kapellenweg 2 b, 78315 Radolfzell, Germany

¹⁷ SMC2 - construction sports et loisirs, Z.A. les Anés, 2 Rue du Chapitre 69126 Brindas, France

¹⁸ University of Duisburg-Essen, Institute for Metal and Lightweight Structures, 45117 Essen, Germany

Abstract

Tensile fabric structures are used for large-scale iconic structures worldwide, yet analysis and design methodologies are not codified in most countries and there is limited design guidance available. Non-linear material behaviour, large strains and displacements and the use of membrane action to resist loads require a fundamentally different approach to structural analysis and design compared to conventional roof structures.

The aim of the round robin analysis exercise presented here is to understand the current state of analysis practice for tensile fabric structures, and to assess the level of consistency and harmony in current practice. The exercise consists of four precisely defined tensile fabric structures, with participants required to carry out the form finding and load analysis of each structure and report key values of stress, deflection and reactions.

The results show very high levels of variability in terms of stresses, displacements, reactions and material design strengths, and highlight the need for future work to harmonise analysis methods and provide validation and benchmarking for membrane analysis software. Greater consistency is required to give confidence in the analysis and design process, to enable third party checking to be carried out in a meaningful and efficient manner, to provide a harmonious approach for Eurocode development, and to enable the full potential of tensile structures to be realised.

Keywords

Membrane structure; tensile fabric; architectural fabric; round robin; comparative analysis; form finding; conic; hypar; Eurocode 10.

1 Introduction

1.1 Background

For over forty years tensile fabric has been used for a wide variety of large scale, architecturally striking structures, including sports stadia, airports and shopping malls [1]. A fabric membrane acts as both structure and cladding, thereby reducing the weight, cost and environmental impact of the construction [2]. Architectural fabrics have negligible bending and compression stiffness, which means that fabric structures must be designed with sufficient curvature to enable environmental loads to be resisted as tensile and shear forces in the plane of the fabric. This contrasts with conventional roofs in which loads are typically resisted by arch action or by stiffness in bending. The shape of the fabric canopy is vital to its ability to resist all applied loads predominantly in tension: to resist both uplift and down-forces (typically due to wind and snow respectively) the surface of the canopy must be double-curved and prestressed. Typically conic or saddle shapes are used to achieve this, taking advantage of their inherent double-curvature (Figure 1). Fabric structures are prestressed to ensure that the fabric remains in tension under all load conditions and to reduce deflections. The low weight of the fabric means that gravity or 'self-weight' loading is often negligible. Consequently, tensile fabric is frequently more structurally efficient and cost-effective for large span roofs than conventional construction methods.

Figure 1. Membrane structures. Hampshire Cricket Club, 2001, (top) – classic tensile architecture consisting of multiple conic canopies (© Buro Happold / Mandy Reynolds); Cayman International School, Cayman Islands, 2006 (centre) – a small, elegant six point hyperboloid (© Architekten-Landrell Associates); Ashford Designer Outlet, Kent, 2000, (bottom) – a dramatic and extensive fabric canopy which combines mast supported high points with ridge and valley cables (© Ben Bridgens)

1.2 Material properties

Architectural fabrics typically consist of woven glass fibre yarns with a polytetrafluoroethylene (PTFE) or Silicone coating, or woven polyester yarns with a polyvinyl chloride (PVC) coating. The woven yarns provide tensile strength, whilst the coating stabilises and protects the weave and provides waterproofing and shear stiffness. The interaction of warp and fill yarns (known as 'crimp interchange', Figure 2) results in complex, non-linear biaxial stress-strain behaviour that cannot directly be inferred from uniaxial test results [3-5]. Under biaxial load the ratio of the applied loads will determine the equilibrium configuration of the crimp. This balancing of the crimp results in a highly variable stiffness and Poisson's ratio. For isotropic, homogeneous solids Poisson's ratio cannot exceed 0.5, however for architectural fabrics higher values are commonly used to model the large negative strains which occur under biaxial load [6]. Use of biaxial fabric test data in structural analysis is typically set within a plane stress framework using elastic moduli and interaction terms [7]. This enables the complex non-linear fabric behaviour to be approximated by parameters that are compatible with available structural analysis software. Inevitably this results in simplification of the non-linear data, with no procedure for quantifying the significance of this simplification to the analysis and design of the structure. Due to the expense of testing, and limited understanding of how to interpret biaxial test results, assumed linear elastic material properties are frequently adopted for analysis and design.

Figure 2. 'Crimp interchange' is the interaction of warp and fill yarns under biaxial load

1.3 Form finding and analysis

The form of a fabric structure cannot be prescribed but must be determined from the geometry of the supporting structure. Early work on fabric structures [8] used soap bubbles to determine this form, in a process known as form finding. To achieve a uniform prestress the fabric must take the form of a

minimal surface. The minimal surface joins the boundary points with the smallest possible membrane area, has uniform in-plane tensile stresses throughout, and is in equilibrium. Prestress can be chosen to be isotropic (equal prestress in warp and fill directions) resulting in a true minimal surface, or for more control of the membrane form the ratio of warp to fill prestress can be varied (anisotropic prestress).

The modeling and analysis of membrane structures is a two-stage process – form finding followed by load analysis - requiring specialist finite element analysis software. For the first stage, boundary conditions (support geometry, fixed or cable edges) and form finding properties (fabric and edge cable prestress forces) are defined. Form finding is independent of the fabric material properties. A soap-film form finding analysis [9] provides the membrane geometry and prestress loads. A new model is created with this updated ('form-found') geometry that is used for the analysis stage. Subsequently the fabric material properties are defined, loads are applied (typically prestress, wind, & snow) and a geometrically non-linear (large displacement) analysis is carried out assuming zero bending and compression stiffness.

The form finding component of membrane structure analysis is not commonly found in other structural analysis software and has led to the development of bespoke analysis methodologies beyond the normal scope of finite element codes. The basis of the geometrically non-linear analysis may be continuum based, use a mesh of discrete elements in the form of cables, or be a combination of both approaches. Finite elements formulated on plane stress principles clearly fall in the continuum-based category, making use of orthotropic material properties including elastic moduli (axial and shear) and Poisson's ratios. Representing the membrane as a cable network with elements aligned in the warp and fill directions with the elastic stiffnesses of the cables taken as the uniaxial stiffness of the fabric in each orthogonal direction, clearly ignores some material interactions, and negates the use of Poisson's ratio and the fabric shear modulus. In combining these two principal approaches, the membrane surface may be subdivided into sets of triplets of arbitrarily orientated geometrically nonlinear cables (or bars) where the axial stiffness (both elastic and geometric) and axial forces of each cable can be determined by treating the area bounded by the triplet of cables as a continuum [e.g. 9, 10]. Some of the cables may be referred to as bars since compressive axial forces may be required in certain instances to represent the continuum stress state. It is a reasonable expectation that these approaches will lead to potentially dissimilar solutions, particularly at the elastic analysis stage.

Due to geometric non-linearity results from different load cases cannot be combined and load factors should not be used [11, Clause 6.3.2]; each combination case (e.g. prestress + wind uplift) is analysed separately and a permissible stress approach is used to assess the required membrane strength [7]. Engineering groups across a range of countries have adopted alternative design stress factors that have been derived using a number of different approaches, with values varying from 3 to 8. Whether or not it is explicitly stated, the magnitude of all of these values is driven by the knowledge that fabric strength is severely reduced by the presence of a tear [12]. The large magnitude of the stress factors, combined with the common misnomer of referring to them as 'safety factors', gives potentially false comfort to the

designer that a large margin of safety has been incorporated in the design, and that this will accommodate any other uncertainties that may not have been explicitly considered.

1.4 Why carry out a round robin exercise?

Tensile fabric structures are used for large-scale iconic structures worldwide, yet analysis and design methodologies are not codified in most countries and there is limited design guidance available [7, 13]. Non-linear material behaviour, large strains and displacements and the use of membrane action to resist loads require a fundamentally different approach to structural analysis and design compared to traditional roof structures. It is well known that several alternative simulation approaches are used, each with particular characteristics and capabilities. Furthermore, there are no benchmarks for membrane structure analysis. Exact analytical solutions are difficult to obtain for form finding and analysis of membrane structures, with limited work to date giving solutions for special cases of cable net and pneumatic structures [8] and mathematically defined minimal surfaces [14].

Against this backdrop of uncertainty, CEN Technical Committee 250 Working Group 5 has started the work of drafting Eurocode 10 for membrane structures. The Eurocode will be expected to include generic guidance on acceptable analysis methodologies, and it is important that the standard reflects current practice. In addition, it is anticipated that the Eurocode will contain Annexes describing multiple, appropriate analysis methodologies in detail. This work is clearly important at the European level, and also internationally given the link between the CEN and ISO organisations through which CEN standards may be adopted worldwide. To achieve a consistent, coherent code some harmonisation of the current analysis methods is required, in particular an understanding of the significance of any differences between existing methods.

A round robin exercise [e.g. 15, 16] refers to an activity such as an experiment, simulation or analysis of data performed independently by multiple institutions. Once the exercise is complete the solutions are reviewed and compared. The exercise presented here was organised by the *TensiNet Analysis and Materials Working Group*. *TensiNet* (www.tensinet.com) is a multi-disciplinary association for all parties interested in tensioned membrane construction, which aims to disseminate best practice in all aspects of membrane structure analysis, design, manufacture and fabrication. The aim of this exercise is to facilitate an understanding of the analysis methodologies used in the design of membrane structures, and to understand any variability introduced by different analysis tools. Four different tensile fabric structures have been defined in detail, with participants required to carry out the form finding and load analysis of each structure and report key values of stress, deflection and reactions. The value of the round robin exercises will be:

1. To understand the level of variability introduced into the design process by the choice of analysis methodology,
2. Development of proposals for improving harmony between analysis methods, including self-checking and benchmarking,

3. The methods used in the round robin exercise may be readily incorporated into Eurocode 10 as indicative analysis approaches,
4. By analysing the same membrane structures it will be possible to see how the analysis is applied to each structure, and to be able to understand what may be expected as outputs from the analysis. This will also prove useful in helping to define the “reporting section” of Eurocode 10,
5. Data from the round robin exercise will be used to identify the material test requirements (e.g. biaxial, shear, tear strength...) as inputs to the particular analysis approaches. This will contribute to the drafting of the testing EN being produced by CEN248 Working Group 4 (Coated Fabrics).
6. Assist in defining the future direction and activities of the *Analysis & Materials Working Group*.

2 Description of the exercises

Four simple, realistic membrane structures have been considered for this round robin exercise. The aim of the exercise is to compare the results of different modelling and analysis techniques. Therefore, the exercises have been defined in sufficient detail to minimise the need for engineering judgement and assumption. For each exercise the following information has been provided (Figure 3 & Figure 4):

- Geometry of support points and definition of boundary conditions (e.g. point support, fixed edge, edge cable).
- Membrane material type (e.g. PVC/polyester, PTFE/glass, silicone/glass) and mechanical properties represented by warp and fill stiffness, Poisson’s ratios and shear stiffness,
- Fabric orientation / patterning direction,
- Fabric (and edge cable) prestress in warp and fill directions,
- Edge cable diameter and material properties (exercises 3 & 4),
- Loading magnitude and direction, and analysis (load combination) cases.

The geometry of the membrane surface has not been provided, but must be determined using a form finding analysis with the support geometry and prestress values as input. The analysis of the membrane structure will be under the assumption of static loads. Other aspects of the analysis methodology are not prescribed, and are expected to be that which the participants normally use in practice.

Particular features have been included in the exercise specification to test the significance of known limitations in certain analysis codes:

- Asymmetric prestress, i.e. differing prestress values in warp and fill directions (exercise 1),
- Specification of shear stiffness and Poisson’s ratio values (all exercises),

- Poisson's ratio greater than 0.5 (exercise 4),
- Inclusion of a structure for which shear stiffness is significant to its structural performance (exercise 4). A hypar structure with two high points and two low points works primarily by spanning between opposite corners, with downward load transferred to the high points and upward load transferred to the low points. To optimise performance the warp and fill directions should run from corner to corner (Figure 4, Exercise 3). For efficiency of manufacturing, or for more complex hypar shapes (Figure 1, centre), the yarn directions may span from edge to edge. In this case the shear stiffness of the material will be critical to the performance of the structure.
- Four independent elastic constants (warp and fill stiffness E_w and E_f , Poisson's ratios for warp-fill and fill-warp interaction, ν_{wf} and ν_{fw}) which do not conform to the reciprocal relationship, i.e. $\nu_{wf} / E_w = \nu_{fw} / E_f$ (exercise 4).

Results of the exercises have been collected on detailed forms which request values of maximum and minimum warp, fill and shear stresses for each analysis case, reactions at specified locations and maximum membrane displacement. Details of the analysis methodology (e.g. name and version of the software, reference or website link describing the basis of the software, etc.), assumptions made to obviate the need for specific data not provided as part of the task specification and reasons for not making use of any part of the information provided as part of the task specification were requested. In addition, the minimum tensile strength of the fabric required to construct each fabric structure was requested, to be accompanied by a statement of the design criteria used to specify the fabric strength.

The specification of required fabric strength is the one output from the round robin that requires independent input from the analyst. The choice and method of application of stress factors is not codified, and values proposed in design guidance vary greatly.

Exercise 1. Conic with asymmetric prestress

Geometry:

14m x 14m square base with fixed edges

Circular head ring: 5m above base, 4m diameter, fixed

Prestress:

Radial (warp) = 4kN/m, circumferential (fill) = 2 kN/m

Material properties: PVC coated polyester,

Warp modulus = 600 kN/m, Fill modulus = 600 kN/m,
Poisson's ratio, $\nu_{wf} = \nu_{fw} = 0.4$, Shear modulus = 30 kN/m

Applied loading:

Uniform wind uplift: 1.0 kN/m² perpendicular to upper surface of fabric

Uniform snow: 0.6 kN/m² vertical downwards

Loadcases for analysis:

LC1: Prestress; LC2: Prestress + Wind uplift; LC3: Prestress + Snow

Note: seams are not required to be modelled

Exercise 2. Conic with equal prestress

As Exercise 1, except:

Geometry:

Circular head ring: 4m above base, 5m diameter, fixed

Prestress:

Radial (warp) = circumferential (fill) = 4 kN/m

Figure 3. Specification of exercise 1 (conic with asymmetric prestress) and exercise 2 (conic with equal prestress in warp and fill directions)

Exercise 3. Simple hypar

Geometry: 6m x 6m square hypar, high points 2m above low points. Warp direction runs between high points. Edges are supported by cables.

Prestress: warp = fill = 3 kN/m; cable prestress = 30kN.

Material properties: PVC coated polyester,

Warp modulus = 600 kN/m, Fill modulus = 600 kN/m,
Poisson's ratio, $\nu_{wf} = \nu_{fw} = 0.4$, Shear modulus = 30 kN/m
Cable diameter = 12mm, axial stiffness equivalent to a solid steel rod, elastic modulus = 205 GPa = 205 kN/mm²

Applied loading:

Uniform wind uplift: 1.0 kN/m² perpendicular to upper surface of fabric

Uniform snow: 0.6 kN/m² vertical downwards

Loadcases for analysis:

LC1: Prestress; LC2: Prestress + Wind uplift; LC3: Prestress + Snow

Note: seams are not required to be modelled

Exercise 4. Twin hypar

Geometry: 12m x 6m twin hypar, 3 high points and 3 low points. 4m height difference between high and low points. Warp direction as shown. Edges are cables supported.

Prestress:

Warp = fill = 5 kN/m; cables prestress = 50 kN

Material properties: PTFE coated glass fibre,

Warp modulus = 1400 kN/m, Fill modulus = 800 kN/m,
Poisson's ratio, $\nu_{wf} = \nu_{fw} = 0.8$, Shear modulus = 100 kN/m
Cable diameter = 19mm, axial stiffness equivalent to a solid steel rod, elastic modulus = 205 GPa = 205 kN/mm²

Applied loading:

Uniform wind uplift: 1.0 kN/m² perpendicular to upper surface of fabric

Uniform snow: 0.6 kN/m² vertical downwards

Loadcases for analysis:

LC1: Prestress; LC2: Prestress + Wind uplift; LC3: Prestress + Snow

Note: seams are not required to be modelled

Figure 4. Specification of exercise 3 (simple hypar) and exercise 4 (twin hypar)

3 Participants

The exercises have been attempted by 22 participants from 20 different organisations (two organisations provided two different solutions), representing fourteen engineering design consultancies and six universities from four countries in Europe, the Middle East, South-East Asia, and the United States (see list of authors and affiliations for details). For such a specialist analysis exercise, this response represents a significant proportion of the organisations that would be capable of carrying out such exercises world-wide. The exercise has been completed with the understanding that it aims to increase the current state-of-the-art of the analysis of membrane structures, and that the results would be disseminated through the activities of Tensinet (www.tensinet.com) and other publications. The exercise was undertaken without fee or liability, and it was agreed that the results would be anonymous. The analysis codes used by the participants are listed in Table 1. The codes are listed in alphabetical order, such that they cannot be related to the participant numbers used in the presentation of the results, to avoid compromising anonymity.

Analysis code	Analysis methodology (details as provided by recipients)	Shear stiffness used	Poisson's ratio used	Poisson's ratio modified in Exercise 4?
3D3S 10.1	Non-linear Finite Element Methods , Equations solved using the Newton-Raphson method; Cable element and Trimesh Element.	NDP	NDP	Yes: $V_{wf} = 0.457$ (Note 2)
Carat++ (carat.st.bv.tum.de)	Form finding using updated Reference Strategy; analysis using geometrical nonlinear membrane elements (large deformations, small strains)	Yes	Yes	Yes: 0.4
EASY 9.2 (www.technet-gmbh.de)	Force density	No	No	NDP
Easy (www.technet-gmbh.de)	Force density	No	No	NDP
GSA 8.5 (www.oasys.com)	Form finding: soap-film with geodesic / ratio spacers to control mesh	Yes	Yes	NDP
GSA 8.5 (www.oasys.com)	Form finding using Dynamic Relaxation; large displacement, small-strain tension only membrane analysis.	Yes	Yes	$V_{fw} = 0.457$ (Note 2)
In house code	No details provided	NDP	NDP	NDP
inTENS v5i	Dynamic relaxation. Triangular constant strain membrane elements	Yes	Yes	NDP
ixForten 4000 release 4.3.6	Force density	No	No	NDP
Mpanel FEA	Geometrically nonlinear solver	NDP	NDP	Yes: $V_{fw}=0.8$ $V_{fw}=0.457$ (Note 2)
Not specified	Form finding using force density cable net. Large displacement, small strain analysis.	Yes	Yes	To suit reciprocal rule
PRISM. VERSION 1.00-03.	3 noded linear stress-strain triangle. Equations are solved using the conjugate gradient method.	NDP	NDP	Yes: $V_{wf} = 0.457$ (Note 2)
Research code	6 node, large strain, linear strain triangle	Yes	Yes	NDP
Rhino-Membrane 1.2.7 (www.ixcube.com)	Rhino-Membrane uses an algorithm based on the update reference strategy. Form finding was run for 200 iterations.	N/A	N/A	N/A
Sofistik 2010	4-node quad-elements with membrane characteristics (only tension, simplified linear-elastic orthotropic material law	Yes	V_{fw} not used	Yes: 0.49
Sofistik Version 2010 (11.10-25)	FE-Analysis : Direct Skyline Solver (Gauss/Cholesky)	Yes	Yes	Yes: 0.4999
Sofistik Version: 11.17-25	No details provided	Yes	Yes	NDP
Strand7	Non-linear analysis, direct sparse matrix	Yes	Yes	Yes: 0.5
TENSYL	Dynamic Relaxation	Yes	Yes	Yes: 0.3
TL_Form & TL_Load	Dynamic Relaxation using simplex elements	Yes	Yes	NDP
TL_Form & TL_Load	Dynamic Relaxation using simplex elements	Yes	Yes	NDP
WinFabric Version 7.2	Force density, Newton Raphson	No	No	NDP
Notes (1) E = elastic modulus, v = Poisson's ratio, w = warp direction, f = fill direction, N/A = not applicable, NDP = no details provided (2) A value of $v_{fw} = 0.457$ complies with the reciprocal rule for the specified values of E_w , E_r and E_{wf} . The specified value of v_{fw} intentionally did not comply.				

Table 1. Analysis codes used by participants in the round robin exercise

4 Results & discussion

4.1 Presentation of results

Numerical responses are presented in the form of box-plots produced using *IBM SPSS Statistics 20*. The dark line within the box represents the median value, with the top and bottom of the box indicating the 75th and 25th percentiles. The whiskers above and below the box extend to the smallest and largest data values that have not been classified as outliers. Outliers are defined as values that are more than 1.5 times the height of the box away from the ends of the box. Circles represent outliers, with stars representing extreme outliers with values removed by more than three times the height of the box. It follows that the whiskers extend approximately 1.5 times the height of the box, with approximately 95% of the data expected to lie between the upper and lower whiskers if the data is normally distributed. Outliers are labelled with the participant number, providing an anonymous reference to a particular analysis. These reference numbers are consistent across all of the results presented. Each graph contains a note of the number of responses (N) that have been analysed for that particular statistic. This number is usually less than the total number of responses because not all respondents were able to provide all of the output that was requested. For example, many analyses do not provide values of shear stress, and some academic institutions have chosen not to supply 'design stresses' as they do not routinely do this. The most significant data has been presented and analysed in this paper; a complete set of original, anonymous data is available from the publisher's website (Table T1).

4.2 Form finding and prestress

Analysis of a form-found structure with prestress loading applied is typically carried out to assess the quality of the form finding process for that structure. If isotropic prestress has been applied and the boundary conditions allow a minimal surface to be achieved, then the stress levels should be equal to the specified prestress and be uniform throughout the membrane, and the displacements should be zero.

If the boundary conditions preclude a minimal surface from being achieved, then specification of anisotropic prestress and/or accepting a poorly converged form finding solution will enable a form to be generated which will have varying levels of prestress at different points on the structure. If this structure is analysed with prestress loading equal to the original, specified prestress values then displacements will occur in order to achieve equilibrium. If the applied prestress values are those determined by the form finding analysis then the structure should be in equilibrium. The choice of whether to apply the specified prestress or the prestress from the form finding analysis was not specified in the exercise, and this distinction is rarely considered in practice.

Seven participants commented that it was impossible to achieve uniform values of prestress for a conic with differing levels of prestress in warp and fill directions, as specified in Exercise 1. *"...it is not possible to generate a doubly curved surface with constant anisotropic prestress distribution, but if the prestress*

is allowed to vary around its mean value, many interesting and physically stable shapes can be generated" [14]. The non-linear change in curvature in the warp (radial) direction results in a non-linear variation in stress from the base of the conic to the head-ring. Two participants stated that the ratio of the warp stresses at the base and head-ring should be approximately equal to the ratio of the length of the boundaries at the base and head-ring. The approximation is due to the base being square rather than circular, resulting in variable curvature around the structure. For the conic described in Exercises 1 and 2 the base is 56.0 m long and the head ring diameter is 12.6 m, giving a ratio of 4.4. This is broadly consistent with the variation in stress levels at prestress, with the maximum warp stress varying from 5.1 to 11.4 kN/m and the minimum from 1.6 to 3.2 kN/m for a target value of 4.0 kN/m.

The variable curvature around the square base should give lower stresses at the corners of the structure where the ratio of curvature between the base and ring will be small (Figure 6 A), and higher stresses on the sides of the structure which have lower curvature (Figure 6 B). On the contrary, for the two examples shown the stresses are higher in the corners suggesting incorrect form finding resulting in the structure primarily spanning along these radial lines rather than achieving uniform load distribution. Boundary conditions for which a minimal surface cannot be achieved, combined with anisotropic prestress, is commonly specified in engineering practice to enable the range of feasible conic forms to be extended to meet architectural requirements [17]. Uniform prestress is frequently assumed for compensation testing and patterning, but often this will not be achieved in practice.

Figure 5. Warp and fill stresses for analysis with prestress loading only; target values (warp, fill in kN/m): exercise 1 = 4, 2; exercise 2 = 4, 4; exercise 3 = 3, 3; exercise 4 = 5, 5.

Figure 6. Two examples of non-uniform stress distribution generated when the conic structure described in exercise 1 is analysed with prestress loading only (warp stress, left; fill stress, right; all units kN/m)

Exercise 2 specifies equal prestress in warp and fill directions, yet there is still considerable spread in the maximum and minimum values; for a target prestress of 4 kN/m the maximum warp stress has a mean value of 5.2 kN/m and a standard deviation of 2.0 kN/m. This demonstrates that even for isotropic prestress many form finding methodologies are not achieving the minimal surface for the specified boundary conditions. It is important to note that the form finding analysis does not utilise the material properties, but is based purely on the boundary geometry and prestress levels.

The hypar described in Exercise 3 is arguably the simplest possible membrane structure, and the prestress values in Figure 5 show a much closer correlation to the target value. Exercise 4 has two bays but is otherwise very similar to Exercise 3, yet even this small increase in complexity gives a sudden divergence from the target prestress values. It is noted that real structures are frequently of much greater complexity than these four exercises, implying potentially greater divergence. Form finding is the one part of the analysis and design process where part of the solution should be known – the aim is to achieve uniform prestress at the target value (or a smooth variation of prestress with changing radius of

curvature for asymmetric prestress). Therefore, the form finding stage may be described as a partial benchmark. The analysis process should start with a check that analysis with prestress loading gives the required prestress, and the variation and distribution of stresses at prestress should ideally be included in the analysis output to facilitate assessment of the quality of the form finding and analysis.

4.3 Membrane stresses under wind and snow loading

Under wind loading the maximum stress values are generally quite consistent (Figure 7). For example the maximum warp stress in Exercise 1 has a mean value of 8.3 kN/m and a standard deviation of 3.1 kN/m. This large standard deviation is caused by a small number of extreme outliers rather than a generally large spread of results. The interquartile range (IR) provides an indication of the level of variability excluding outliers, with a value of 1.1 kN/m for the Exercise 1 maximum warp stress. There are instances which show much greater variability, such as in exercise 2, for example, where the maximum fill stress has a mean of 12.0 kN/m and an IR of 3.1 kN/m. The variability of minimum stresses is even greater; exercise 1 minimum fill stress has a mean value of 1.6 kN/m and IR of 2.1 kN/m, and this is fairly typical of exercises 1, 2 and 4. One of the design requirements for tensile fabric structures is to avoid the membrane becoming slack, as this can potentially lead to flapping, creasing and even structural instability. It is therefore significant that the variation in minimum stress is large, with some participants predicting zero stress (i.e. slack fabric), where the majority concurred that the structure remains in tension under all load conditions. This would lead to some designers deeming the structure to be unsuitable for construction and requiring design changes, with others proceeding with installation.

Snow loading shows even greater stress variability than wind loading, with the distribution and variability of results differing significantly between exercises and load cases (Figure 8). Given that the exercises are well defined structures with simple geometry the variability is very large. For each output parameter a measure of variability is given by dividing the interquartile range by the mean; for example for maximum warp stress due to snow load this gives $4.4/14.0 = 31\%$. The average of this measure for all output shown in Figure 8 is 44%. A key problem in assessing these results is that the correct values are not known. Given the high level of problem definition there should be a unique value for each output, but there is no reason to think that the mean, median or any other value is necessarily correct. With many analysis codes based on similar approaches, it may be that an outlying value, if generated by a single analysis code using a theory more representative of the membrane structure physics, is actually correct. This lack of benchmarks and validation is a key problem for the advancement of the field.

Figure 7. Warp and fill stresses for load case 2 – uniform wind uplift

Figure 8. Warp and fill stresses for loadcase 3 – uniform snow load

4.4 Stress factors and specified fabric strength

For the design of membrane structures the maximum warp and fill stresses are typically multiplied by stress factors to determine the required fabric strength (Figure 9 and Table 2). Combining the varied warp and fill stresses from the analyses (Figure 7 & Figure 8) with a wide range of different stress factors inevitably results in a large range of required material strengths (standard deviation varying from 13 to 39 kN/m for mean values around 40 to 60 kN/m, and the average interquartile range is 37% of the overall mean). A wide range of design codes and guidance were referenced by participants (Table 2), with nine participants using 'in-house' values. Even participants using the same design guidance for the same structures derived different stress factors, showing that interpretation is not necessarily straightforward, and any future guidance or standardisation must be clear and robust.

Figure 9. Required fabric strengths specified for each exercise

Source	Stress factor		Notes (interpreted from information provided by participants)
	Wind (LC2)	Snow (LC3)	
French design guide [18]	4.44	4.44	Quality factor (1.0) x area factor (0.9) x original factor security for medium pollution (4)
	4.5	4.5	
	5.0	5.0	
ASCE 55-10 [13]	4.0	5.0	For prestress only (LC1), stress factor = 8
Tensinet Design Guide [7, Chapter 6]	6.0	6.0	Value for permanent structures
Italian standard [19]	4.5	3.75	Load factor (1.5) x material factor (3 for wind or 2.5 for snow)
DIN 1055-100 for load safety factors with material safety factor according to Minte [7, Section 6.2.3, 20]	≈ 3.24	≈ 5.51	Factors: (1.35 x prestress) + (1.5 x wind or snow). Material safety factor prestress + snow = 3.67, prestress + wind = 2.16
DIN 4134 [21] with reduction factors according to Minte [7, Section 6.2.3, 20]	5.3 (Ex.1), 6.2 (Ex.2), 4.6 (Ex.3), 7.1 (Ex.4)		Factors vary for each exercise and loadcase dependent on load duration and direction (higher factors for fill stresses to account for seams)
	4.4	4.4	Material factor (1.4) x load factor (1.5) x reduction factors (1.1 x 1.2 x 1.6)
Chinese Technical Standard [22]	5.0	5.0	Factor for simultaneous wind and snow would be 2.5
In house practice	4.0	5.0	Based on ASCE 55-10 [13]
	4.0	4.0	Based on Tensinet Design Guide [7, Chapter 6]
	3.5	2.75	
	5.0	5.0	
	3.0	3.0	
	6.0	6.0	Tear propagation (4) x material variability (1.25) x long term use (1.2)
	5.0	6.0	
	3.05	4.85	e.g. for Snow: material factor (1.4) x Load factor (1.5) x Biaxial load (1.2) x Long term loading (1.6) x Pollution/degradation (1.2)
	5.0	6.0	
Maximum / minimum	7.1 / 3.0	7.1 / 2.8	
Mean (standard deviation)	4.7 (1.0)	5.0 (1.0)	

Table 2. Stress factors for determination of required fabric strength

4.5 Shear

Shear stresses and strains are rarely reported in fabric structure design, but shear strains are generated during installation to enable a structure with double curvature to be developed from flat panels. Subsequently displacements under load will result in further shear strain. It is generally considered that fabrics have limiting values of shear strain beyond which the shear stiffness increases and the fabric will tend to wrinkle [23, 24]. For this reason it is common practice to use materials with softer coating (PVC-

polyester or silicone-glass) for structures with high levels of double curvature, and to reduce panel widths for stiffer materials (PTFE-glass) to reduce the magnitudes of shear deformation during installation.

Shear stress values were reported by 17 participants, with no shear information available from discrete analyses that do not consider shear stiffness. Exercise 4 was intentionally specified to provide a structure that utilises the shear stiffness of the material to span between pairs of high and low points. The result was a larger variation in shear stress than for the other exercises (Figure 10). Excluding outliers, the shear stress for Exercise 4 ranged from zero to 5.1 kN/m, which equates to shear angle of zero to 2.9°. This variability, combined with a lack of knowledge about fabric shear behaviour, means that it is extremely difficult for a design engineer to make meaningful choices about patterning and design based on shear stress and strain output, and highlights the need for further work in this area.

Figure 10. Maximum shear stress for loadcase 2 (L2, wind uplift) and loadcase 3 (L3, snow); a shear stress of 1 kN/m equates to a shear strain of 1.9° for exercises 1 to 3, and 0.57° for exercise 4 which specified a higher value of shear stiffness.

4.6 Displacements under wind and snow loading

Maximum displacement values are more consistent than stress values for most exercises and load cases (Figure 11), with the average interquartile range equal to 25% of the mean. However, this still represents a significant range of values and even for the simplest hypar structure (exercise 3) has an interquartile range of 48mm, and included two extreme outliers with values approximately five times the mean. Fabric structure design practice does not impose strict deflection limits, as large movements are not necessarily problematic. Whilst deflection limits are typically considered to be a serviceability condition, avoidance of clashing with structural elements, ponding and slackness could all result in

failure of the membrane structure. In these situations deflection requirements must be considered to be an ultimate limit state, and should be calculated to a correspondingly appropriate level of accuracy using appropriate safety factors.

Figure 11. Maximum vertical displacement at any point on the structure; L2 and L3 denote loadcases 2 (wind) and loadcase 3 (snow)

4.7 Support reactions

The substantial variability of warp and fill stresses discussed above inevitably results in highly variable support reactions (Figure 12). The design of the supporting structure is fundamental to the efficiency, cost and elegance of a lightweight structure. High support reactions will increase the size of edge cables and connection details, which are often costly stainless steel components. Large connections and oversize steelwork will severely detract from both the overall aesthetic quality of the structure, and will impact on the potential economic and environmental benefits of this form of construction.

Figure 12. Total support reactions for conic structures (exercises 1 and 2); L2 and L3 denote loadcases 2 (wind) and loadcase 3 (snow). Refer to Figure 3 for locations of support reactions R1 and R2.

Figure 13. Total support reactions for hypar structures (exercises 3 and 4); L2 and L3 denote loadcases 2 (wind) and loadcase 3 (snow). Refer to Figure 4 for locations of support reactions R1 to R3.

For a simple hypar (exercise 3) the majority of participants provided highly consistent support reactions (Figure 13), but even for this simple structure the overall range of values is large. The two-bay, six-point hypar analysed for exercise 4 relies on shear stiffness to span between high and low points. By excluding shear the fabric spans primarily between the cable supported edges. The type of analysis impacts on the action of the structure, and it follows that the support reactions are more variable than in exercise 3.

4.8 Influence of analysis type

From the participants' descriptions of their analysis software (Table 1) the responses have been divided into two categories: 'continuum analysis' in which the fabric acts as a continuum and shear stiffness and Poisson's ratio are considered, and 'discrete analysis' methods which model the fabric as a grid of cables and shear and Poisson's effects are ignored (Figure 14, Figure 15 & Figure 16). Stress levels show a broadly similar overall range of values for the two analysis types (Figure 14). The continuum results show a high level of consistency between the majority of participants with a small number of outliers, whereas the discrete analysis results show a similar level of variation from only a small number of participants (i.e. very limited consensus between participants).

Figure 14. Comparison of maximum warp and fill stresses for two analysis types

The difference between the two analysis methodologies is clear when displacements are considered (Figure 15). For conic structures (exercises 1 and 2) there is little difference in the results between the analysis types, but for hypars (exercises 3 and 4) the discrete analyses give much greater variability. The importance of the choice of analysis methodology for hypar structures is further emphasised by the support reactions, which show much greater variability for the discrete analysis (Figure 16).

For exercise 4 the continuum analyses use a range of values of Poisson's ratio (from 0.3 to 0.8, Table 1), but the variability in stress, displacement and reaction values is low, and no greater than for other loadcases. This is consistent with previous work [17] which found that membrane structure analysis typically has limited sensitivity to variations in Poisson's ratio, and suggests that the key difference between the continuum and discrete analyses is the omission of shear stiffness from the latter.

Figure 15. Comparison of displacements for two analysis types

Figure 16. Comparison of support reactions for hypar structures for two analysis types

5 Conclusions

When the round robin exercise was launched, the organisers received several comments of the form: *“Why are you doing this? - the exercises are so well defined that it is inevitable that everyone will get the same results”*. The results presented above clearly justify the need for an exercise of this type, and the need for future work to harmonise analysis methods and provide validation and benchmarking for membrane analysis software. Consistency is required to give confidence in the analysis and design process, to enable third party checking to be carried out in a meaningful and efficient manner, to provide a more harmonious approach for Eurocode development, and to enable safe and efficient structures to be constructed.

The results show very high levels of variability in terms of stresses, displacements, reactions and material design strengths. For most output parameters there is a wide spread of values. It is difficult to generalise but the standard deviation and the interquartile range are both commonly 25 - 50% of the mean value. Extreme outliers are present in almost every output that has been considered, and these suggest errors at some stage in the analysis process – this may be in the problem set-up, analysis code itself, interpretation of the results or reporting. With typically two or three extreme outliers for any

reported value, it is clear that rigorous checking procedures should be implemented for membrane structures to prevent severe under- or over-design.

Analysis of simple, well defined structures at prestress showed large variations in stress levels. It is clear that in exercise 1 an equilibrium surface cannot be achieved with the specified prestress and boundary conditions. In cases such as this, the actual prestress values may be considerably higher than the specified values. Actual prestress values from the analysis, rather than the specified values, should be used for compensation testing and patterning, particularly (but not exclusively) for structures with anisotropic prestress. The range and distribution of stresses from analysis at prestress should always be included in the analysis output. Comparison of prestress levels with the target values provides the only currently available method of checking the quality of the form finding and analysis – but this check is only valid if a minimal surface can be achieved for the specified boundary conditions and prestress. The difficulties in form finding which occurred with exercise 1, and the subsequent variability in analysis results, highlights the importance of engineers working closely with architects during the initial design phases to ensure that the desired form can be achieved efficiently. There are software packages available that are aimed specifically at this process and facilitate form finding and conceptual design of lightweight structures (e.g. formfinder, www.formfinder.at).

For certain structures, in particular multi-point hypars (e.g. Figure 1, centre), the choice of patterning direction combined with the treatment of shear stiffness in the analysis leads to fundamental changes in the behaviour of the structure, which results in large variations in the support reactions. Accurate calculation of support reactions is vital to ensure efficient, elegant, safe design of connection details and supporting structure. It is important for designers to understand which structures are sensitive to patterning and shear, to use appropriate analysis tools for these structures, and to ensure that the patterning direction is maintained and communicated from analysis through design to construction.

The overall range of stress factors used by participants to determine the required material strength is 2.8 to 7.1. This range is very large, and clearly some standardisation is required to enable meaningful design checks to be carried out, and for a consistent level of safety and efficiency to be provided in fabric structures.

Throughout the analysis of the round robin results the clear problem has been that the ‘correct’ values are not known. Benchmark structures with known forms and stress distributions are required to enable validation of analysis codes, but the development of these benchmarks is not straightforward. Checking the analysis at prestress for structures with isotropic prestress levels is straightforward, as the correct unique minimal surface form will give uniform prestress levels equal to the target value. Beyond this, for anisotropic prestress and for load analysis the solutions are not known. The exercises have shown that use of a simple hypar for testing or benchmarking of an analysis tool is not sufficient – this test may be passed but any increase in complexity can result in rapidly divergent output.

The tasks used for this round robin were precisely defined, with fully specified geometry, material properties and loading. In reality, both the material properties and loading may be less well defined and

their determination requires considerable engineering judgement. Material properties involve design and specification of non-standard tests and interpretation of complex, non-linear test data to provide values of elastic constants for analysis. Wind and snow loading codes do not include provision for the complex forms typical of fabric architecture, and only the largest projects can afford bespoke wind tunnel testing. Further round robin exercises are proposed on interpretation of material test data and calculation of structural loading to provide a full picture of the variability inherent in current fabric structure design practice.

Supplemental material

Table T1: complete, anonymous data from the round robin exercise is available on the publisher's website in Comma Separated Variable (.csv) format.

Acknowledgements

The authors would like to express their gratitude to all participants who spent considerable time completing the analysis exercises without any form of payment. Participants' details are included in the list of authors, and in addition Y. Zhao (Beijing Space Frame Consulting Engineering Co., Ltd., B6101 Wangjing Tower, Chaoyang District, Beijing, P.R.China, 100102) took part in the exercise.

The authors would like to thank Tensinet (www.tensinet.com) for facilitating the organisation of the round robin through meetings of the Analysis & Materials Working Group and publicising the exercise.

This research was carried out without financial support.

Bibliography

- [1] Berger H. Form and function of tensile structures for permanent buildings. *Engineering Structures*. 1999;21:669-79.
- [2] Bridgens BN, Gosling PD, Birchall MJS. Tensile fabric structures: concepts, practice & developments. *The structural engineer: journal of the Institution of Structural Engineers*. 2004;82:21-7.
- [3] Peirce FT. The Geometry of cloth structure. *Journal of the Textile Institute*. 1937;28:81-8.
- [4] Skelton J. Mechanical properties of coated fabrics. In: Hearle J, Thwaites J, Amirbayat J, Rijn A, editors. *Mechanics of Flexible Fibre Assemblies*. Netherlands: Sijthoff & Noordhoff; 1980. p. 461-9.
- [5] Tan K, Barnes M. Numerical representation of stress-strain relations for coated fabrics. *IStructE symposium on design of air supported structures*. Bristol1980.
- [6] Bridgens BN, Gosling PD, Birchall MJS. Membrane material behaviour: concepts, practice & developments. *The structural engineer: journal of the Institution of Structural Engineers*. 2004;82:28-33.
- [7] Forster B, Mollaert M. Design guide for tensile surface structures. Brussels: Tensinet; 2004.
- [8] Otto F. Pneumatic structures. *Tensile structures*. Cambridge, Massachusetts: M.I.T. Press; 1967.
- [9] Barnes M. Form finding and analysis of tension structures by dynamic relaxation. *International Journal of Space Structures*. 1999;14:89-104.
- [10] Gosling PD, Zhang L. A High-Fidelity Cable-Analogy Continuum Triangular Element for the Large Strain, Large Deformation, Analysis of Membrane Structures. *Cmes-Computer Modeling in Engineering & Sciences*. 2011;71:203-51.
- [11] BSi. Eurocode - Basis of structural design. BS EN 1990:2002 + A1:2005. Brussels: British Standards Institute; 2002.
- [12] Happold E, Ealey TA, Liddell WI, Pugh JW, Webster RH. Discussion: The design and construction of the Diplomatic Club, Riyadh. *The structural engineer : journal of the Institution of Structural Engineers*. 1987;65A:377-82.
- [13] ASCE/SEI. 55-10: Tensile Membrane Structures. 2010.
- [14] Linhard J, Bletzinger K-U. "Tracing" the Equilibrium - Recent Advances in Numerical Form Finding. *International Journal of Space Structures*. 2010;25:107-16.
- [15] Jhung MJ, Kim SH, Choi YH, Chang YS, Xu X, Kim JM et al. Probabilistic Fracture Mechanics Round Robin Analysis of Reactor Pressure Vessels during Pressurized Thermal Shock. *J Nucl Sci Technol*. 2010;47:1131-9.
- [16] Rueschoff J, Kerr KM, Buettner R, Olszewski WT, Alves VA, Grote HJ et al. Round Robin Test to Evaluate the Reproducibility of a Therapeutically Relevant Immunohistochemical Score for the Categorization of Non-Small Cell Lung Cancer (NSCLC) Into Tumours With High and Low Epidermal Growth Factor Receptor (EGFR) Expression. *European Journal of Cancer*. 2011;47:S592-S.
- [17] Bridgens BN, Gosling PD, Patterson CH, Rawson SJ, Hove N. Importance of material properties in fabric structure design & analysis. In: Domingo A, Lazaro C, editors. *IASS Symposium 2009: Evolution and Trends in Design, Analysis and Construction of Shell and Spatial Structures*. Valencia2009. p. 2180-91.
- [18] ITBTP. Recommendation pour la conception des ouvrages permanents de couverture textile. *Annales des Batiments et Travaux Publics*. Modified 1998 ed1997.
- [19] UNI. EN 13782:Temporary Structures - Tents - Safety. 2006.
- [20] Minte J. Das mechanische Verhalten von Verbindungen beschichteter Chemiefasergewebe: Aachen; 1981.
- [21] DIN. Tragluftbauten - DIN 4134. 1983.
- [22] CECS. 158: Technical Specification for Membrane Structures. China2004.
- [23] Pargana JB, Lloyd-Smith D, Izzuddin BA. Advanced material model for coated fabrics used in tensioned fabric. *Engineering Structures*. 2007;29:1323-36.
- [24] Skelton J. Shear of woven fabrics. In: Hearle J, Thwaites J, Amirbayat J, Rijn A, editors. *Mechanics of Flexible Fibre Assemblies*. Netherlands: Sijthoff & Noordhoff; 1980. p. 211-27.